

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 10-283840

(43)Date of publication of application : 23.10.1998

(51)Int.Cl.

H01B 1/16
H01B 5/12
H05K 1/09
H05K 1/11

(21)Application number : 09-098367

(71)Applicant : MITSUBOSHI BELTING LTD

(22)Date of filing : 31.03.1997

(72)Inventor : YAGIYUU HIROMASA
KAWAHARA MASATO
NOGUCHI TORU

(54) COPPER CONDUCTOR PASTE FOR ALUMINUM NITRIDE BOARD, AND ALUMINUM NITRIDE BOARD

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a copper conductor paste which adheres satisfactorily even to an aluminum nitride board and provide such an aluminum nitride board using the copper conductor paste.

SOLUTION: Particulates are formed from copper, copper oxide, or mixture thereof whose mean particle size ranges between 1-500 nm, and a mixture copper powder is prepared by adding to the particulates the base copper powder as chief component with the mean particle size ranging between 0.5-10 μ m and one sort or more of aux. copper powder having a smaller mean particle size, and therefrom a copper conductor paste is formed together with a binder resin, glass powder, and organic solvent, wherein the binder resin should consist of a resin having at least a pyrolytic temp. of 250-350°C, and the glass powder has a softening point lower than the sintering point of the particulates or mixture copper powder and higher than the decomposing temp. of the binder resin.

LEGAL STATUS

[Date of request for examination]

22.04.2003

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than
the examiner's decision of rejection or
application converted registration]

[Date of final disposal for application]

[Patent number] 3756283

[Date of registration] 06.01.2006

[Number of appeal against examiner's
decision of rejection]

[Date of requesting appeal against examiner's
decision of rejection]

[Date of extinction of right]